INFLUENCE OF BACKGROUND AND CEMENT SHADES ON THE COLOR OF LOW-TRANSLUCENCY LITHIUM-DISILICATE CERAMICS

Mohammed Zahran¹*, Dania Sabbahi², Areej Abdulgader³, Hanan Alrowithi⁴, Mona Aqely⁵, Alshaymaa Faydhi⁶, Shahad Rushan³

¹ Oral and Maxillofacial Prosthodontics Department, Faculty of Dentistry, King Abdulaziz University, Jeddah, Saudi Arabia. ² Dental Public Health Department, Faculty of Dentistry, King Abdulaziz University, Jeddah, Saudi Arabia . ³ Princess Nourah University, Riyadh, Saudi Arabia. ⁴ Private Practice, Jeddah, Saudi Arabia . ⁵ Al-Mikhwah Dental Center, Al-Baha, Saudi Arabia. ⁶ University Dental Hospital, King Abdulaziz University, Jeddah, Saudi Arabia.

ABSTRACT

Statement of the Problem: Matching adjacent anterior all-ceramic restorations supported by natural teeth and implants to adjacent natural teeth or all-ceramic restoration is a demanding task for both clinicians and dental technician, especially when cemented to natural teeth and/or implant-supported abutments with different stump shades.

Aim: To compare the optical effect of dissimilar background and cement shades in terms of color differences (ΔE) after cementation to low-translucency lithium-disilicate glass-ceramic (LT-LDGC).

Material and Methods: Sixty LT-LDGC specimens were sectioned from CAD/CAM block with a standard thickness of (1.5 ± 0.2) mm. Four background materials (zirconia (white), nano-ceramic filled composite resin (shade A2), dual-cure composite core build-up (shades light opaque and A3) were used to fabricate rectangular square discs (n=15). Ceramic and background specimens were cemented with three shades of dual-cure self-adhesive resin cement (clear, white, and yellow). The 3 coordinates of the CIELAB system were measured using a spectrophotometer (Vita Easyshade Advance, Vita Zahnfabrik) twice (at baseline for the ceramic alone and after cementation). Then, color difference (ΔE_{00}) values were calculated for each sample with the baseline measurement as control. Two-way ANOVA was used to analyze the effect of the background and cement shade on the color difference at a significant level (0.05).

Results: Two-way ANOVA revealed a significant effect of the background shade, but not for the cement shade and their interaction on the color difference. The reported ΔE_{00} values ranged between 2 to 8.5. Majority of the groups showed ΔE_{00} values higher than clinically acceptable level ($\Delta E_{00} > 2.25$). Only one group of the combination of zirconia background and yellow cement showed means ΔE_{00} values within the clinically acceptable level ($1.3 < \Delta E_{00} \le 2.25$).

Conclusion: This study demonstrated that the underlying background color influences the final color of the LT-LDGC restorations. Using variable cement shades failed in decreasing the color difference to a clinically acceptable level.

Key words: Background, Cement, Color, Ceramics, Spectrophotometer.

INTRODUCTION

Metal-free dental ceramic materials were introduced into the field of dentistry by McLean since 1965. ¹ Advancements in the ceramic industry improved our armamentarium with the introduction of ceramic restorations with optimal esthetics and mechanical properties. These advancements allow clinicians to meet their patients' demands and expectations.² However, dentists are often challenged with cases that involve matching single anterior tooth or implant-supported all-ceramic restorations to adjacent natural dentition, especially in the anterior zone. ³ This can be even more

challenging when the case is involving a combination of natural dentition and implant-supported restorations as a result of different background colors. ⁴⁻⁷ Till recently, metalbased cement or screw-retained implant-supported restorations were the standard treatment option available for dental implants. Matching the color of metal-based to allceramic restorations can be challenging due to the dark color of the metal substructure. The introduction of strong ceramics, such as yttrium-stabilized zirconium oxide polycrystals (Y-TZP) materials allows a clinician to deliver implant-supported restorations with highly esthetic outcome and enhance the color matching to adjacent teeth. ⁸ These zirconia-based abutments are often combined with cementretained all-ceramic crowns. Lithium disilicate is one of the most commonly used dental ceramics for this purpose due to their high mechanical properties and superior esthetics as a result of their optimal translucency which allows better light transmission thought the restoration. ⁹ Matching ceramic restorations made using these translucent ceramics with natural teeth is very challenging and cannot be ensured, ¹⁰ especially when cemented to natural teeth and/or implantsupported abutments with different stump shades.

Several factors might affect the final color of all-ceramic restoration. These factors can be divided into three main categories: ceramic-related, substrate-related, and cement-related. ^{11, 12} These factors include background color, luting cement color, and ceramic thickness. Having a dark background color (e.g. metal-based implant abutment, abutment teeth with intrinsic dark staining or metal cast post and core) would result in darker final restoration, and vice versa.^{6, 10, 13} Several studies evaluated the effect of luting cement shade on the final restoration color and concluded that using the opaquer shade of luting cement will help in masking the underlying dark substrate. ^{5, 7}

Color matching in dentistry can be achieved either visually through the use of available shade guides (subjective method) or electronically by using instrument-based shade selection (objective method). Variety of dental shade matching devices have been introduced to overcome the limitations of the visual shade matching including, spectrophotometers, colorimeters, and imaging systems. Spectrophotometers are one of the most accurate and flexible instruments for color matching in dentistry. ¹³ They measure the energy of the transmitted or reflected light from an object at 1-25 nm intervals along the visible spectrum. ¹⁴ Compared to the subjective conventional method, spectrophotometers offered a 33% elevation in accuracy and a more objective match in 93.3% of cases. ¹⁴ The Commission Internationale de l'Eciairage (CIE) method was used frequently in the dental research to explain the relationship between color difference and their perception and acceptance in clinical practice. 15

The purpose of this in-vitro study is to determine the color difference using a variety of background shades and resin luting cement and their influence in approaching clinical reality. The null hypothesis was that there is no significant effect of the background shade and luting cement shade and their interaction on the color of low-translucent lithium disilicate glass-ceramic (LT-LDGC).

MATERIALS AND METHODS

All the materials used in the study and their specifications were listed in (Table 1).

Specimen Preparation

LT-LDGC blocks (IPS-e.max®CAD, Size C-14, Ivoclar/Vivadent, Liechtenstein) were sectioned to produce 60 ceramic rectangular specimens (15.75mm*14.25mm*1.5mm) utilizing diamond wafering blade (4"*0.012") (UKAM Industrial Superhard Tools Valencia, USA) mounted on a slow-speed saw (Isomet 2000 Precision Saw, Buehler, USA).

Four different background groups were used to fabricate rectangle specimens (n=15/group). The specimens of the 1st (ZR) and 2nd (A3) groups were sectioned from zirconium-(IPS e.max ZirCAD, Size C15, oxide blocks Ivoclar/Vivadent) and composite blocks (Lava Ultimate, shade A3, 3M ESPE, Germany), respectively, using a diamond wafering blade (4"*0.012") (UKAM Industrial Superhard Tools Valencia) mounted on a slow-speed saw (Isomet 2000 Precision Saw, Buehler). While, the specimens for the 3rd and 4th groups were fabricated from dual-cure composite core build-up material (LuxaCore Z-Dual, DMG, Germany) using light opaque (LO) and (A3) shades, respectively. The LuxaCore material was injected in a custom mold that was created using putty PVS material (Take 1 Advanced[™] Putty, Kerr Corp., USA) utilizing lithium disilicate rectangular specimens (15.75mm*14.25mm*1.5mm). Then, cured using LED curing light (Bluephase N, Ivoclar/Vivadent) for a total of 40 seconds (20 sec/side).

All background and LT-LDGC specimens were polished using assorted silicon carbide sandpaper of different grits (220, 320, 400, and 600, sequentially) (ACE Hardware Corp., Oak Brook, IL, USA). After polishing, the specimens' thicknesses (listed in Table 1) were verified using a digital caliper (Mitutoyo Corporation, Tokyo, Japan). ZR group specimens' thicknesses were increased by 25% to accommodate for the anticipated shrinkage after sintering. LT-LDGC and ZR group specimens were crystalized/sintered according to manufacturer's instructions using a porcelain furnace (Programat® EP 3010, Ivoclar/Vivadent) and a high-temperature furnace (Sintramat, Ivoclar Vivadent), respectively.

Cementation Procedures

The four background groups (A2, A3, LO, and ZR) were cemented to their corresponding LDGC specimens using self-adhesive dual-cure resin cement (Maxcem Elite Chroma, Kerr, U.S.A) with three different shades of cement; clear, white and yellow.

A standardized weight of 64g was applied over the ceramic/background complex during cementation To standardize the cement layer thickness for 5 min, followed by light curing using an LED light cure unit (Bluephase N, Ivoclar/Vivadent) for a total of 40 seconds (20 sec/side).

Spectrophotometric Measurement

A digital spectrophotometer (VITA Easyshade; VITA Zahnfabrik, Bad Säckingen, Germany) was used to record the color coordinates in the CIE (Commission International de l'Eclairage) Lab color space system. A custom-made square box of 6 cm³ lined with a black interior with an opening hole in the top of the box to accommodate the tip of the spectrophotometer during measurement.

Two spectrophotometric readings were recorded for each specimen, for ceramic specimens alone (S1) as a baseline and the ceramic-background complex after cementation (S2), respectively. All recorded data were organized and tabulated in an excel sheet (Microsoft Excel for Mac, version 16.10, 2017) to be prepared for statistical analysis.

To determine the effect of changing the background and the shade of the cement, color difference was calculated using the CIEDE2000 (ΔE_{00}) according to the following formula:

 $\Delta E_{00} = \sqrt{\left(\frac{\Delta L'}{K_{v} S_{v}}\right)^{2} + \left(\frac{\Delta C'}{K_{v} S_{v}}\right)^{2} + \left(\frac{\Delta H'}{K_{w} S_{w}}\right)^{2} + R_{T} \left(\frac{\Delta C'}{K_{w} S_{v}}\right) \left(\frac{\Delta H'}{K_{w} S_{v}}\right)}$

Where:

 $\Delta C'$, $\Delta L'$, and $\Delta H'$: differences in chroma, lightness, and hue.

RT: rotation function which accounts for the interaction between chroma and hue differences within the blue region.

 S_L , S_C , and S_H : weighting functions that adjust the total color difference for variation in the location of the color difference pair in L, a, b coordinates.

 K_L , K_C , and K_H : parametric correction factors for experimental conditions.

The parametric factor of the CIEDE2000 color-difference formula was set to 1. While, the clinical acceptability threshold was set at ΔE_{00} >2.25 units, and the perceptibility threshold was set at ΔE_{00} =1.30. ^{16, 17}

Statistical Analyses

Two-way analysis of variances (ANOVA), followed by Tukey's post-hoc comparisons, was used to evaluate the effect of the background color, cement shade and their interaction on the color difference (ΔE_{00}). All statistical analyses were two-tailed and conducted using the SPSS software for Windows (version 20, SPSS Inc., IBM, Somers, New York, USA) at a significance level of (0.05).

RESULTS

Two-way ANOVA revealed a significant effect of the background, but not for cement shade and the interaction term, on the color difference (Table 2).

Material and Manufacturer	Lot No.	Thickness (mm)	Shade	Туре
LuxaCore Z-Dual	7(2200	10 17	T * 1.	
(LU)	/63208	1.3 – 1.7	Light opaque	~
(DMG, Germany)				Composite core build-up
LuxaCore Z-Dual				Bis-GMA resin matrix)
(A3)	779562	1.5	A3	
(DMG, Germany)				
IPS-e.max ZirCad				
(ZR)	L 12762	15	White	Yttrium-stabilized zirconiu
Ivoclar/vivadent,	L13/03	1.5	white	oxide
Liechtenstein				

Table 1: Characteristics of the materials used in this study

Source	Type III Sum of Squares	df	Mean Square	F	Sig.
Corrected Model	304.029	11	27.639	25.938	<0.001
Intercept	1932.451	1	1932.451	1813.542	< 0.001
Background	297.300	3	99.100	93.002	< 0.001
Cement	3.037	2	1.518	1.425	0.251
Background * Cement	3.692	6	.615	.577	0.746
Error	51.147	48	1.066		
Total	2287.627	60			
Corrected Total	355.176	59			

Table 2: Two-way ANOVA (dependent variable: ΔE_{00} *; independent variables: background and cement shade).* R Squared = 0.856 (Adjusted R Squared = 0.823)

The mean color differences (ΔE_{00}) of different groups in comparison to the baseline measurement are reported in (Table 3). The reported ΔE_{00} values ranged between 2 to 8.5. Most of the groups showed ΔE_{00} values higher than clinically acceptable level ($\Delta E_{00} > 2.25$). Only one group of the combination of ZR background and yellow cement showed mean ΔE_{00} value within the clinically acceptable level (1.3 < $\Delta E_{00} \le 2.25$).

Background	Cement Shade					
Dackground	Clear	White	Yellow			
A2	7.9 (1.9) ^c	7.3 (0.6)°	7.1 (0.8) ^c			
A3	8.2 (1.0) ^c	8.5 (0.8)°	7.7 (1.6) ^c			
Luxacore (Lo)	4.4 (0.8) ^b	4.6 (0.7) ^b	4.7 (1.3) ^b			
Zirconia	2.7 (0.5) ^{a, b}	3.0 (0.8) ^{a, b}	2.0 (0.5) ^a			

Table 3: Mean (SD) for ΔE_{00} for different groups in the study (Results of Tukey post-hoc comparisons are shown as superscript letters, and values having the same superscript letters were not significantly different (P>.05))

DISCUSSION

The null hypothesis of the present study was partially rejected. The results revealed that the color perception of different background shades showed a statistically significant difference, while, the influence of cement shade and the interaction term were not statistically significant.

The structure of the lithium disilicate ceramic affects its optical properties. The presence of lithium disilicate crystalline phase dispersed in the glassy matrix allows the light to pass through ceramic without scattering, which might result in a reflection of the underlying background shade. ⁷ The findings of the present study confirmed that and revealed higher ΔE_{00} for the samples fabricated using A2 and

A3 backgrounds as compared to the samples fabricated using ZR and LO backgrounds. This could be attributed to the white color of the ZR and LO backgrounds which reflect all the light that passes through the LT-LDGC compared to the darker backgrounds (A2 and A3) which reflect less and absorb more light. This finding is in agreement with previous studies. ^{5, 6, 18}

In the present study, changing the cement shade did not mask the effect of the background color and did not help in tuning it significantly. This finding is in agreement with the results reported in a previous study. ⁴ On the contrary, a previous work that used a similar methodology reported a significant effect of the cement on the color difference. ¹⁸ This disagreement can be explained by the differences in the translucency of the glass-ceramic used in these studies. The present study used low-translucent in comparison to hightranslucent glass-ceramic in the former study. LT-LDGC is expected to reflect more and pass less light to the underlying structure, which can mask the effect of the cement shade.

Three different shades of cement were used in the current study; yellow, clear, and white, which represents the range of shades available for dual-cure cement produced by different manufacturers. It is not clear whether using different cement brands might change the results of the study. This can be the main focus of future research.

In the present study, all the ceramic-cement-background combinations, except one, showed a high mean ΔE_{00} values that can be detected easily as clinically unacceptable ($\Delta E_{00} > 2.5$). The only combinations that revealed a clinically acceptable difference were zirconia background with yellow cement combined with LT-LDGC with $\Delta E_{00} = 2$. This can be explained by the fact that yellow cement shade tuning of the highly reflective white background to match the color of the A3 ceramic. One of the other suggested solutions to

42

overcome the high reflection of the white zirconia background is using different shades of zirconia or using an LDGC abutment attached to titanium base with a shade matching the all-ceramic crown.

Similar to low-translucent LDGC, the high-translucent version of LDGC failed to mask the color of the underlying background and cement combinations. ¹⁸ It seems that high and low translucent ceramics are not the material of choice in cases that involve abutments with a variety of stump shades since they have limited ability to mask the underlying substructure. ^{19,20} Alternatively, using high opacity (HO) and medium opacity (MO) ceramic as a core structure veneered by veneering porcelain can be considered to provide better masking for the underlying background-cement combination and allow better shade matching. ⁷

In the current study, the clinically relevant ceramic thickness was selected as recommended by the manufacturer for allceramic lithium disilicate crowns. Increasing the ceramic thickness to 2.5 mm was found to improve color matching.⁴ This increase might not be feasible in lots of situations and will contradict the concepts of conservative dentistry.

CONCLUSION

Within the limitation of this study, it seems that matching the color of adjacent LDGC restorations using LT ceramic is a difficult task. Varying the cement hue did not help to reduce the disparity in color between different substructure groups to a clinically acceptable level. Future research should focus on the effect of using opaque LDGC and different zirconia shades on the color matching.

REFERENCES

- Kelly JR, Nishimura I, Campbell SD. Ceramics in dentistry: Historical roots and current perspectives. J Prosthet Dent. 1996;75(1):18–32.
- 2. Kelly JR. Dental ceramics: Current thinking and trends. Dent Clin North Am. 2004; 48 (2): 513–30.
- Korfage A, Raghoebar GM, Meijer HJA, Vissink A. Patients' expectations of oral implants: A systematic review. Eur J Oral Implantol. 2018. Vol. 11, p. s65–76.
- Jirajariyavej B, Wanapirom P, Anunmana C. Influence of implant abutment material and ceramic thickness on optical properties. J Prosthet Dent. 2018;119(5):819– 25.
- Dede DÖ, Armağanci A, Ceylan G, Celik E, Cankaya S, Yilmaz B. Influence of implant abutment material on the color of different ceramic crown systems. J Prosthet Dent. 2016;116(5):764–9.

- Al Ben Ali A, Kang K, Finkelman MD, Zandparsa R, Hirayama H. The effect of variations in translucency and background on color differences in CAD/CAM lithium disilicate glass ceramics. J Prosthodont. 2014;23(3):213–20.
- Chaiyabutr Y, Kois JC, LeBeau D, Nunokawa G. Effect of abutment tooth color, cement color, and ceramic thickness on the resulting optical color of a CAD/CAM glass-ceramic lithium disilicate-reinforced crown. J Prosthet Dent. 2011;105(2):83–90.
- Shenoy A, Shenoy N. Dental ceramics: An update. J Conserv Dent. 2010;13(4):195.
- Gracis S, Thompson V, Ferencz J, Silva N, Bonfante E. A New Classification System for All-Ceramic and Ceramic-like Restorative Materials. Int J Prosthodont. 2016; 28(3):227–35.
- Begum Z, Chheda P, Shruthi CS, Sonika R. Effect of Ceramic Thickness and Luting Agent Shade on the Color Masking Ability of Laminate Veneers. J Indian Prosthodont Soc. 2014;14:46–50.
- Barão VAR, Gennari-Filho H, Goiato MC, Dos Santos DM, Pesqueira AA. Factors to achieve aesthetics in allceramic restorations. In: Journal of Craniofacial Surgery. J Craniofac Surg. 2010; 21(6):2007–12.
- 12. Stevenson B, Ibbetson R. The effect of the substructure on the colour of samples/restorations veneered with ceramic: A literature review. J Dent. 2010;38(5):361-8.
- 13. Chu SJ, Trushkowsky RD, Paravina RD. Dental color matching instruments and systems. Review of clinical and research aspects. J Dent. 2010;38 Suppl 2:e2-e16
- Paul S, Peter A, Rodoni L, Pietrobon N. Conventional visual vs spectrophotometric shade taking for porcelainfused-to-metal crowns: A clinical comparison. Int J Periodontics Restorative Dent. 2004;24:222–31.
- 15. Westland S. Review of the CIE System of Colorimetry and Its Use in Dentistry. J Esthet Restor Dent. 2003;15(s1): S5–12.
- Perez Mdel M, Ghinea R, Herrera LJ, Ionescu AM, Pomares H, Pulgar R, Paravina R. Dental ceramics: a CIEDE2000 acceptability thresholds for lightness, chroma and hue differences. *J Dent.* 2011;39 Suppl 3:e37-e44.
- 17. Ghinea R, Pérez MM, Herrera LJ, Rivas MJ, Yebra A, Paravina RD. Color difference thresholds in dental ceramics. J Dent. 2010;38 Suppl 2:e57-e64.
- Zahran M, Sabbahi D, Alghamdi A, Al-Otaibi A, Altaefi B, Baessa L, Bahha L, Influence Of Background And Cement Shades On The Color Of High-Translucency Lithium-Disilicate Ceramics. Ann Dent Spec. 2020;8(1):62–6.

- 19. Heffernan MJ, Aquilino SA, Diaz-Arnold AM, Haselton DR, Stanford CM, Vargas MA. Relative translucency of six all-ceramic systems. Part I: core materials. J Prosthet Dent. 2002;88(1):4-9.
- 20. Li Q, Yu H, Wang YN. Spectrophotometric evaluation of the optical influence of core build-up composites on all-ceramic materials. Dent Mater. 2009;25(2):158-6

CORRESPONDING AUTHOR

Mohammed Zahran

Faculty of Dentistry, King Abdulaziz University, 3527 Abdullah Alsulaiman St. Jeddah 22252 Saudi Arabia **Email:** mzahran@kau.edu.sa